

# Ride-A-Way™

## Specialized Lane Delineation

# PRODUCT DATA

Product Type: Ride-A-Way™ Coatings  
 Product Code: RAW410023 (Neutral Colored Base - Parts A & B)  
 Product Colors: E-F Bike Lane Green\*, Terra Cotta(bus lanes), Red, Blue  
 Effective Date: March 2014

### Product Description:

Ride-A-Way™ coatings are advanced waterborne coatings that combine color fast acrylic resins and an advanced epoxy modification to provide long lasting, color stable, lane delineation.

Ride-A-Way™ features anti-slip properties specially designed to add friction for pedestrians and bicyclists without creating trip hazards. It has excellent adhesion and flexibility properties, and will not crack, peel or flake off the substrate. Ride-A-Way™ is extremely chemical resistant as it is impervious to gas, oil and de-icing agents.

Ride-A-Way™ is recommended for long lane, no to low traffic delineation areas for preferential use such as bike lane, bus lane, medians, no stopping areas and pedestrian zones.

### Product Advantages:

- **Durable.** Epoxy crosslinking provides increased durability over typical waterborne coatings, especially in wet climates.
- **Flexible.** Coatings can easily expand and contract with the asphalt substrate.
- **Non-slip.** Friction properties designed for pedestrians and cyclists.
- **Color stable.** No noticeable color change due to UV stability.
- **Chemical resistant.** Impervious to gas, oil and de-icing agents.
- **Environmentally friendly.** Low VOC waterborne coating that can be recycled with the substrate.
- **Extends the life of the substrate.** Protects the pavement from typical weathering effects.

### Packaging:

One unit of Ride-A-Way™ consists of:

- 5 gallon pail of Part A
- 1 Quart container of Part B
- 1 Quart or 1 Pint container of colorant

Each mixed unit of Ride-A-Way™ coatings will cover approximately 175 sq. ft. (16.3 m<sup>2</sup>) using the recommended 4-layer system. While building the coating in layers, there will be less coverage with the first layer and greater coverage with subsequent layers.

### Storage:

Keep materials between 40-90F. Do not freeze or expose to excessive heat.

### Other:

Use recommended primer for application onto concrete substrates.



Product Characteristic		Test
Density	13.3 lbs/gal	ASTM D 1475
Solids by volume	55% +/- 2%	ASTM D 2697
Solids by weight	70% +/-2%	ASTM D 2369
Dry Time (to recoat)	~35 min	ASTM D 5895 (23°C; 37% RH)
Taber Wear Abrasion - Dry H-10 wheel	≤ 0.98 g/1000 cycles	ASTM D 4060 (1 day cure)
Taber Wear Abrasion - Wet H-10 wheel	≤ 3.4 g/1000 cycles	ASTM D 4060 (7 day cure)
Water Absorption	~8.3%	ASTM D 570 (9 days immersion)
Shore Hardness	~60	ASTM D 2240 Type D
Mandrel Bend	1/4 in @ 21° C	ASTM D 522-93A
Permeance	3.45 g/m <sup>2</sup> /hr	ASTM D 1653
VOC	<20 g/l	ASTM D 3960-05
Adhesion to asphalt	Substrate Failure	ASTM D 4541
Friction (Wet)	>60 BPN	ASTM E 303

\*FHWA compliant color for bike lanes

The product data offered herein is, to the best of our knowledge, true and accurate, but all recommendations are made without warranty, expressed or implied. Because the conditions of use are beyond our control, neither Ennis-Flint nor its agents shall be liable for any injury, loss or damage, direct or consequential, arising from the use or the inability to use the product described herein. As Ennis-Flint has neither control over the installation of product described herein nor control of the environmental factors the installed markings are subjected to, there is no guarantee as to the durability or the retroreflective properties of any marking system applied. No person is authorized to make any statement or recommendation not contained in the Product Data, and any such statement or recommendation, if made, shall not bind the Corporation. Further, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents, and no license under the claims of any patent is either implied or granted.



**ENNIS-FLINT**  
A Traffic Safety Solutions Company

800.331.8118

sales@ennisflint.com

www.ennisflint.com

© Ennis-Flint. All Rights Reserved

032714